

## “Devilab Shadow Satin” Certificate Of Analysis

Code	SHADOW_SATIN			
Basic parameters	Test Method	Specification	unit	Test result
Color	Visual Inspection	Matte	/	Matte
Liner PET Film Thickness	GB/T 6672-2001	85±3	µm	88
Products Total Thickness	GB/T 6672-2001	185±5%	µm	192
Glossy	Gloss Meter @60°	<20	/	13.8
UV Rejection	LS182 Test Meter	>90	/	98.2
QUV ageing resistant	ASTM G154-16 circulation 1	ΔE*ab<2	/	0.23
Hydrophobic	Mark Pen / Water	Hydrophobic	/	Hydrophobic
Surface permeability resistance	MG-2110 Mark pen,10safter alcohol wipe	slight/no trace	/	slight traces
Thermal self-healing	Brass brush 10 times, 50-70°C hot water 1min	100% self- healing	/	100% self-healing
Acrylic layer peeling force/20min	GB/T 2792	>600	gf/inch	1710
Acrylic layer peeling force/24h	GB/T 2792	>1000	gf/inch	2073
Tear strength	GB/T 529	≥40	KN/m	60.3
Elongation at break of coating	GB/T 1040.1	>70	%	77
Tensile Strength	GB/T 1040.1	>15	Mpa	32.3
Elongation at break of PPF	GB/T 1040.1	>200	%	487.3
100% modulus	GB/T 1040.1	>5	Mpa	5.8

**Remark :**

1. Total thickness means: top coating+TPU film+adhesive
2. QUV The aging resistance test duration is 1000h.